

## TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRICS

	Unit	Norm	Value	Tolerance
<b>Weight</b>	<b>g/sqmt</b>	UNI EN ISO 2286-2	<b>2500</b>	<b>± 250</b>
<b>Gauge</b>	<b>mm</b>	UNI EN ISO 2286-3	<b>2.00</b>	<b>± 0,25</b>
<b>Tensile strength warp/weft</b>	<b>N/5cm</b>	UNI EN ISO 1421	<b>≥ 3000</b>	
<b>Adhesion of plies</b>	<b>N/cm</b>	Int. Novurania I0409	<b>≥ 75</b>	
<b>Working temperature</b>	<b>°C</b>		<b>-20 +120</b>	
<b>State of delivery</b>				<b>cured</b>

## CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
<b>Type of yarn</b>	<b>CO</b>	<b>(4 plies)</b>
<b>Construction</b>	<b>Ne</b>	<b>12/2 16 x 15</b>

## CHARACTERISTICS OF COATING ELASTOMER

<b>Type of elastomer</b>	<b>NBR</b>
<b>Colour</b>	<b>black</b>
<b>Compound approved for regulation</b>	<b>R67/2</b>