

## TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRIC

	Unit	Norm	Value	Tolerance
<b>Weight</b>	<b>g/sqmt</b>	UNI EN ISO 2286-2	<b>2850</b>	<b>+/- 300</b>
<b>Gauge</b>	<b>mm</b>	UNI EN ISO 2286-3	<b>2.00</b>	<b>+/- 0,20</b>
<b>Tensile strength warp &amp; weft</b>	<b>N/5cm</b>	UNI EN ISO 1421	<b>≥1800/ ≥1400</b>	
<b>Coating fabric/adhesion</b>	<b>N/5cm</b>	Int. Novurania 10396	<b>≥100</b>	
<b>Working temperature</b>	<b>°C</b>		<b>-30 +90</b>	
<b>State of delivery</b>			<b>cured</b>	

## CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
<b>Type of yarn</b>		<b>VI</b>
<b>Weight</b>	<b>g/m<sup>2</sup></b>	<b>400</b>
<b>Construction</b>	<b>dtex</b>	<b>500/2 20 x 16</b>

## CHARACTERISTICS OF COATING ELASTOMER

<b>Type of polymer</b>	<b>NBR - PVC</b>
<b>Colour</b>	<b>red</b>

## APPLICATIONS

Fabric to membranes complying to the R67/ 2 and EN 549, suitable for gas and fuel.

*Novurania declines any responsibility for any damage or problem coming from a wrong usage of the product.*

Issuing date 16<sup>th</sup> of July 2014

Revision: 1