

TT 1040 B

5186030, 5186033

TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRIC

	Unit	Norm	Value	Tolerance
Weight	g/sqmt	UNI EN ISO 2286-2	560	+/- 40
Gauge	mm	UNI EN ISO 2286-3	0,45	+/- 0,05
Tensile strength warp/weft	N/5cm	UNI EN ISO 1421	≥900/ ≥900	
Tear strength warp/weft	N	DIN 53356 B	≥25/ ≥15	
Coating/fabric adhesion	N/5cm	Int. Novurania 10396	≥ 70	
Dimensional variation after aging warp/weft	%	Int. Novurania 10405	≤±1 / ≤±1	
Flame behaviour	-	DIN 53438-T3	F2	
Working temperature	°C		-40 +120	
State of delivery			cured	

CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
Type of yarn		PA
Weight	g/sqmt	110
Construction	dtex	235 19 x 19

CHARACTERISTICS OF COATING ELASTOMER

Type of elastomer	BIIR
Colour	green RAL 7013