

## TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRIC

	Unit	Norm	Value	Tolerance
<b>Weight</b>	<b>g/sqmt</b>	UNI EN ISO 2286-2	<b>560</b>	<b>+/- 40</b>
<b>Gauge</b>	<b>mm</b>	UNI EN ISO 2286-3	<b>0,45</b>	<b>+/- 0,05</b>
<b>Tensile strength warp/weft</b>	<b>N/5cm</b>	UNI EN ISO 1421	<b>≥900/ ≥900</b>	
<b>Tear strength warp/weft</b>	<b>N</b>	DIN 53356 B	<b>≥25/ ≥15</b>	
<b>Coating/fabric adhesion</b>	<b>N/5cm</b>	Int. Novurania 10396	<b>≥ 70</b>	
<b>Dimensional variation after aging warp/weft</b>	<b>%</b>	Int. Novurania 10405	<b>≤±1 / ≤±1</b>	
<b>Flame behaviour</b>	<b>-</b>	DIN 53438-T3	<b>F2</b>	
<b>Working temperature</b>	<b>°C</b>		<b>-40 +120</b>	
<b>State of delivery</b>			<b>cured</b>	

## CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
<b>Type of yarn</b>		<b>PA</b>
<b>Weight</b>	<b>g/sqmt</b>	<b>110</b>
<b>Construction</b>	<b>dtex</b>	<b>235 19 x 19</b>

## CHARACTERISTICS OF COATING ELASTOMER

<b>Type of elastomer</b>	<b>BIIR</b>
<b>Colour</b>	<b>sand</b>