

TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRIC

	Unit	Norm	Value	Tolerance
Weight	g/sqmt	UNI EN ISO 2286-2	1050	+/- 100
Gauge	mm	UNI EN ISO 2286-3	0,80	+/- 0,08
Tensile strength warp/weft	N/5cm	UNI EN ISO 1421	≥3000/ ≥3000	
Tear strength warp/weft	N	DIN 53356 B	≥60/ ≥60	
Coating/fabric adhesion	N/5cm	Int. Novurania 10396	≥ 65	
Dimensional variation after aging warp/weft	%	Int. Novurania 10405	≤±1 / ≤±1	
Flame behaviour	-	DIN 53438-T3	F1	
Working temperature	°C		-40 +120	
State of delivery			cured	

CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
Type of yarn		PA
Weight	g/sqmt	260
Construction	dtex	940 11 x 12

CHARACTERISTICS OF COATING ELASTOMER

Type of elastomer	BIIR
Colour	sand