

## TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRICS

	Unit	Norm	Value	Tolerance
<b>Weight</b>	<b>g/sqmt</b>	UNI EN ISO 2286-2	<b>1350</b>	<b>+/- 200</b>
<b>Gauge</b>	<b>mm</b>	UNI EN ISO 2286-3	<b>1,20</b>	<b>+/- 0,15</b>
<b>Tensile strength warp/weft</b>	<b>N/5cm</b>	UNI EN ISO 1421 mod provini da 15x200 mm	<b>≥7500/ ≥7000</b>	
<b>Elongation at break warp/weft</b>	<b>%</b>	UNI EN ISO 1421 mod provini da 15x200 mm	<b>30 / 43</b>	<b>+/- 3</b>
<b>Adhesion</b>	<b>N/5cm</b>	Int. Novurania 10396	<b>≥ 100</b>	
<b>Working temperature</b>	<b>°C</b>		<b>- 20 +120</b>	
<b>State of delivery</b>			<b>cured</b>	

## CHARACTERISTICS OF TEXTILES REINFORCEMENT

	Unit	Value
<b>Nature of yarn</b>		<b>PA</b>
<b>Weight</b>	<b>g/sqmt</b>	<b>485</b>
<b>Construction</b>	<b>dtex</b>	<b>1880 13 x 13</b>

## CHARACTERISTICS OF COATING ELASTOMER

<b>Type of polymer</b>	<b>CSM</b>
<b>Colour of rubber</b>	<b>white (food grade side)</b>

## APPLICATIONS

**Enological membranes**