

# TT 3005 G

5155379

## TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRICS

	Unit	Norm	Value	Tolerance
<b>Weight</b>	<b>g/sqmt</b>	UNI EN ISO 2286-2	<b>1450</b>	<b>+/- 200</b>
<b>Gauge</b>	<b>mm</b>	UNI EN ISO 2286-3	<b>1,35</b>	<b>+/- 0,15</b>
<b>Tensile strength warp &amp; weft</b>	<b>N/5cm</b>	UNI EN ISO 1421	<b>≥5500/ ≥4500</b>	
<b>Elongation at break warp &amp; weft</b>	<b>%</b>	UNI EN ISO 1421	<b>≤35/ ≤35</b>	
<b>Coating/fabric adhesion</b>	<b>N/5cm</b>	Int. Novurania 10396	<b>≥ 125</b>	
<b>Working temperature</b>	<b>°C</b>		<b>- 20 +100</b>	
<b>State of delivery</b>			<b>cured</b>	
<b>Finishing surface</b>			<b>fabric impression</b>	

## CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
<b>Type of yarn</b>		<b>PA</b>
<b>Weight</b>	<b>g/sqmt</b>	<b>390</b>
<b>Construction</b>	<b>dtex</b>	<b>940 20 x 20</b>

## CHARACTERISTICS OF COATING ELASTOMER

<b>Type of elastomer</b>	<b>CR</b>
<b>Colour</b>	<b>black</b>

## APPLICATION

**Oil booms, hovercrafts skirts**

Issuing date 11<sup>th</sup> of April 2011

Revision: 2