

TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRIC

	Unit	Norm	Value	Tolerance
Weight	g/sqmt	UNI EN ISO 2286-2	890	+/- 90
Gauge	mm	UNI EN ISO 2286-3	0.60	+/- 0.06
Tensile strength warp & weft	N/5cm	UNI EN ISO 1421	≥1300/ ≥1000	
Elongation at break warp & weft	%	UNI EN ISO 1421	32/ 36	+/- 5
Tear strength warp & weft	N	ISO 4674/1977 A.2.2.2	≥400/ ≥300	
Coating adhesion	N/5cm	Int. Novurania I0396	≥ 100	
Working temperature	°C		-20 +120	
State of delivery			cured	

CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
Type of yarn		PA
Weight	g/sqmt	94
Construction	dTex	235 22 x 17

CHARACTERISTICS OF COATING ELASTOMER

Type of polymer	CSM outside layer/ CR inside layer
Colour	choice

APPLICATIONS

Nautical applications

Novurania declines any responsibility for any damage or problem coming from a wrong usage of the product.

Issuing date 19th of June 2015

Revision: 1