

## TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRICS

	Unit	Norm	Value	Tolerance
<b>Weight</b>	<b>g/sqmt</b>	UNI EN ISO 2286-2	<b>1350</b>	<b>+/- 135</b>
<b>Gauge</b>	<b>mm</b>	UNI EN ISO 2286-3	<b>1,00</b>	<b>+/- 0,10</b>
<b>Tensile strength warp &amp; weft</b>	<b>N/5cm</b>	UNI EN ISO 1421	<b>≥4500/ ≥4500</b>	
<b>Elongation at break warp &amp; weft</b>	<b>%</b>	UNI EN ISO 1421	<b>25</b>	<b>+/- 5</b>
<b>Coating/fabric adhesion</b>	<b>N/5cm</b>	Int. Novurania 10396	<b>≥ 100</b>	
<b>Working temperature</b>	<b>°C</b>		<b>- 20 +120</b>	
<b>State of delivery</b>			<b>cured</b>	

## CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
<b>Type of yarn</b>		<b>PES</b>
<b>Weight</b>	<b>g/sqmt</b>	<b>355</b>
<b>Construction</b>	<b>dtex</b>	<b>1670 10 x 10</b>

## CHARACTERISTICS OF COATING ELASTOMER

<b>Type of elastomer</b>	<b>CSM (side A) – NBR food grade (side B)</b>
<b>Colour</b>	<b>green (side A) – cream (side B)</b>

## APPLICATION

**Drinking water tank.**

Issuing date 18<sup>th</sup> of July 2014

Revision: 0