

TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRIC

	Unit	Norm	Value	Tolerance
Weight	g/sqmt	UNI EN ISO 2286-2	4350	+/- 435
Gauge	mm	UNI EN ISO 2286-3	3.40	+/- 0.35
Tensile strength warp & weft	N/5cm	UNI EN ISO 1421	≥11500/ ≥10000	
Elongation at break warp & weft	%	UNI EN ISO 1421	25 / 25	+/- 5
Coating fabric/adhesion	N/5cm	Int. Novurania 10396	≥100	
Working temperature	°C		-10 +90	
State of delivery			cured	

CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
Type of yarn		PES (2 plies)
Weight	g/sqmt	460
Construction	dtex	2200 9.5 x 9.5

CHARACTERISTICS OF COATING ELASTOMER

Type of elastomer	CSM outside layer/ CR inside layer
Colour	various colours

APPLICATIONS

Nautical applications

PROVISIONAL DATA SHEET

Novurania declines any responsibility for any damage or problem coming from a wrong usage of the product.

Issuing date 11th of May 2015

Revision: 0