

## TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRIC

	Unit	Norm	Value	Tolerance
<b>Weight</b>	<b>g/sqmt</b>	UNI EN ISO 2286-2	<b>1400</b>	<b>+/- 140</b>
<b>Gauge</b>	<b>mm</b>	UNI EN ISO 2286-3	<b>1.00</b>	<b>+/- 0.10</b>
<b>Tensile strength warp &amp; weft</b>	<b>N/5cm</b>	UNI EN ISO 1421	<b>≥5000/ ≥4700</b>	
<b>Elongation at break warp &amp; weft</b>	<b>%</b>	UNI EN ISO 1421	<b>25 / 25</b>	<b>+/- 5</b>
<b>Coating fabric/adhesion</b>	<b>N/5cm</b>	Int. Novurania 10396	<b>≥100</b>	
<b>Working temperature</b>	<b>°C</b>		<b>-10 +90</b>	
<b>State of delivery</b>			<b>cured</b>	

## CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
<b>Type of yarn</b>		<b>PES</b>
<b>Weight</b>	<b>g/sqmt</b>	<b>350</b>
<b>Construction</b>	<b>dtex</b>	<b>1670 10 x 10</b>

## CHARACTERISTICS OF COATING ELASTOMER

<b>Type of elastomer</b>	<b>CSM outside layer/ CR inside layer</b>
<b>Colour</b>	<b>various colours</b>

## APPLICATIONS

**Heavy tube fabric**

*Novurania declines any responsibility for any damage or problem coming from a wrong usage of the product.*

Issuing date 18th of May 2015

Revision: 0