



514x550

TT 3033 G

TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRIC

	Unit	Norm	Value	Tolerance
Weight	g/sqmt	UNI EN ISO 2286-2	1000	+/- 100
Gauge	mm	UNI EN ISO 2286-3	0,75	+/- 0.08
Tensile strength warp & weft	N/5cm	UNI EN ISO 1421	≥2500/ ≥2300	
Elongation at break warp & weft	%	UNI EN ISO 1421	20 / 20	+/- 5
Coating fabric/adhesion	N/5cm	Int. Novurania 10396	≥75	
Working temperature	°C		-10 +90	
State of delivery			cured	

CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
Type of yarn		PES
Weight	g/sqmt	240
Construction	dtex	1100 8.5 x 8.5

CHARACTERISTICS OF COATING ELASTOMER

Type of elastomer	CSM outside layer/ CR inside layer
Colour	various colours

APPLICATIONS

Tube fabric Hypair D

Novurania declines any responsibility for any damage or problem coming from a wrong usage of the product.

Issuing date 18th of May 2015

Revision: 0

I0160-0 form schede tecniche Novurania

1 di 1