

## TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRIC

	Unit	Norm	Value	Tolerance
<b>Weight</b>	<b>g/sqmt</b>	UNI EN ISO 2286-2	<b>1090</b>	<b>+/- 110</b>
<b>Gauge</b>	<b>mm</b>	UNI EN ISO 2286-3	<b>0.75</b>	<b>+/- 0.08</b>
<b>Tensile strength warp &amp; weft</b>	<b>N/5cm</b>	UNI EN ISO 1421	<b>≥1250/ ≥1100</b>	
<b>Elongation at break warp &amp; weft</b>	<b>%</b>	UNI EN ISO 1421	<b>20/ 23</b>	<b>+/- 5</b>
<b>Tear strength</b>	<b>N</b>	UNI EN 1875-3	<b>≥120/ ≥100</b>	
<b>Coating adhesion warp &amp; weft</b>	<b>N/5cm</b>	Int. Novurania I0396	<b>≥ 100</b>	
<b>Working temperature</b>	<b>°C</b>		<b>-10 +90</b>	
<b>State of delivery</b>			<b>cured</b>	

## CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
<b>Type of yarn</b>		<b>PES</b>
<b>Weight</b>	<b>g/sqmt</b>	<b>100</b>
<b>Construction</b>	<b>dTex</b>	<b>280 18 x 17</b>

## CHARACTERISTICS OF COATING ELASTOMER

<b>Type of polymer</b>	<b>CSM outside layer/ CR inside layer</b>
<b>Colour</b>	<b>choice</b>

## APPLICATIONS

Nautical applications

### PROVISIONAL DATA SHEET

*Novurania declines any responsibility for any damage or problem coming from a wrong usage of the product.*

Issuing date 19<sup>th</sup> of June 2015

Revision: 0