

TECHNICAL CHARACTERISTICS OF RUBBER COATED FABRICS

	Unit	Norm	Value	Tolerance
Weight	g/sqmt	UNI EN ISO 2286-2	560	+/- 30
Gauge	mm	UNI EN ISO 2286-3	0,60	+/- 0,05
Solvent loss	%	Int. Novurania I0400	≤ 4	
Hardness	shore A		90	
Working temperature	°C		-20 +120	
State of delivery			uncured	

CHARACTERISTICS OF TEXTILE REINFORCEMENT

	Unit	Value
Type of yarn		CO
Weight	g/sqmt	230

CHARACTERISTICS OF COATING ELASTOMER

Type of elastomer	NBR
Colour	brown

APPLICATIONS

O-Rings with high hardness